

Haydite Sieve Analysis Report

**A Hydraulic Press Brick Company**

Brooklyn, IN

Date 2/26/2003

Customer

Wt per CF	49.8	damp loose
Wt per CY	1343	damp loose
Moisture	6.58%	
FM	2.96	

Type Inventory

Screen	Wt. (gm)	% Ret	% Cum	% Pass	ASTM C-331	Limit Check
No4	10.71	1.86%	1.86%	98.14%	85-100	Okay
No8	117.13	20.37%	22.23%	77.77%		
No16	135.79	23.62%	45.85%	54.15%	40-80	Okay
No30	102.84	17.89%	63.74%	36.26%		
No50	78.15	13.59%	77.33%	22.67%	10-35	Okay
No100	45.05	7.83%	85.16%	14.84%	5-25	Okay
No200	20.66	3.59%	88.75%	11.25%		
Pan	64.66	11.25%	100.00%	0.00%		
<b>Total</b>	574.97	<b>IntWt</b> 615.24	<b>DryWt</b> 577.25	<b>Residual</b> 0.39%	.3% loss Limit	

Note

