

Haydite Sieve Analysis Report



Hydraulic Press Brick Company

Brooklyn, IN

Date 2/26/2003

Customer

Wt per CF	49.6	damp loose
Wt per CY	1339	damp loose
Moisture	6.40%	
FM	3.15	

Type Inventory

Screen	Wt. (gm)	% Ret	% Cum	% Pass	ASTM C-331	Limit Check
No4	11.42	1.98%	1.98%	98.02%	85-100	Okay
No8	134.40	23.29%	25.27%	74.73%		
No16	144.19	24.99%	50.26%	49.74%	40-80	Okay
No30	104.23	18.06%	68.33%	31.67%		
No50	73.72	12.78%	81.10%	18.90%	10-35	Okay
No100	39.18	6.79%	87.89%	12.11%	5-25	Okay
Pan	69.85	12.11%	100.00%	0.00%		
<b>Total</b>	576.98					
		<b>IntWt</b> 618.76	<b>DryWt</b> 581.53	<b>Residual</b> 0.78%		.3% loss Limit

Note

