

Haydite Sieve Analysis Report

B-pw Hydraulic Press Brick Company

Brooklyn, IN

Date 2/26/2003

Customer

Wt per CF	49.4	damp loose
Wt per CY	1334	damp loose
Moisture	27.45%	
FM	5.44	

Type Inventory

Screen	Wt. (gm)	% Ret	% Cum	% Pass	ASTM C-331	Limit Check
3/8 in	19.04	3.83%	3.83%	96.17%	80-100	Okay
No4	317.77	63.90%	67.72%	32.28%	5-40	Okay
No8	109.49	22.02%	89.74%	10.26%	0-20	Okay
No16	20.48	4.12%	93.86%	6.14%	0-10	Okay
No30	7.25	1.46%	95.32%	4.68%		
No50	4.93	0.99%	96.31%	3.69%		
No100	3.59	0.72%	97.03%	2.97%		
Pan	14.79	2.97%	100.00%	0.00%		
Total	497.32	IntWt 636.52	DryWt 499.42	Residual 0.42%		.3% loss Limit

Note

