

Haydite Sieve Analysis Report

**C-pw Hydraulic Press Brick Company**

Brooklyn, IN

Date 2/26/2003

Customer

Wt per CF	45.3	damp loose
Wt per CY	1224	damp loose
Moisture	21.90%	
FM	6.04	

Type Inventory

Screen	Wt. (gm)	% Ret	% Cum	% Pass	ASTM C-331	Limit Check
1/2 in	13.80	2.77%	2.77%	97.23%	90-100	Okay
3/8 in	119.49	23.96%	26.73%	73.27%	40-80	Okay
No4	288.27	57.81%	84.53%	15.47%	0-20	Okay
No8	61.16	12.26%	96.80%	3.20%	0-10	Okay
No16	5.84	1.17%	97.97%	2.03%		
No30	2.06	0.41%	98.38%	1.62%		
No50	0.44	0.09%	98.47%	1.53%		
No100	0.29	0.06%	98.53%	1.47%		
Pan	7.33	1.47%	100.00%	0.00%		
<b>Total</b>	498.67	<b>IntWt</b> 608.85	<b>DryWt</b> 499.47	<b>Residual</b> 0.16%		.3% loss Limit

Note Inventory



