

Haydite Sieve Analysis Report

C Hydraulic Press Brick Company

Brooklyn, IN

Date 2/26/2003

Customer

Wt per CF	39.6	damp loose
Wt per CY	1070	damp loose
Moisture	6.24%	
FM	6.18	

Type Inventory

Screen	Wt. (gm)	% Ret	% Cum	% Pass	ASTM C-331	Limit Check
1/2 in	19.38	3.62%	3.62%	96.38%	90-100	Okay
3/8 in	153.68	28.70%	32.32%	67.68%	40-80	Okay
No4	295.29	55.14%	87.46%	12.54%	0-20	Okay
No8	58.90	11.00%	98.46%	1.54%	0-10	Okay
No16	2.39	0.45%	98.90%	1.10%		
No30	0.93	0.17%	99.08%	0.92%		
No50	0.30	0.06%	99.13%	0.87%		
No100	0.20	0.04%	99.17%	0.83%		
Pan	4.43	0.83%	100.00%	0.00%		
Total	535.50	IntWt 565.28	DryWt 532.07	Residual -0.65%		.3% loss Limit

Note



